

LaHabra® Acrylic Bonder

Increase bond strength between the base and cementitious stucco.

LaHabra® Acrylic Bonder increases bond strength and improves physical strength: Two products in one. As a bond enhancer, apply it over a clean base before the cementitious stucco finish is applied. Use it as an admixture mixed directly into the stucco color coat to increase physical strength. For maximum performance, use it both ways.



- Greater Bond Strength
- Greater Physical Strength
- Better Color Uniformity



LaHabra

LaHabra® Acrylic Bonder

Architectural Specification Guide



Description

Use: When used as an intermediate bonding agent, LaHabra® Acrylic Bonder improves bond strength between a cementitious base and stucco finish coat. When used as an additive to the cementitious finish coat it improves its physical strength.

Composition

LaHabra Acrylic Bonder is a water dispersion of acrylic polymers designed for mixing with cementitious coatings.

Packaging

Product is available in gallon bottles, packed four to the case.

Storage

LaHabra® Acrylic Bonder should be stored under cool, dry conditions away from direct sunlight. Properly stored LaHabra® Acrylic Bonder has a useable lifetime of approximately one (1) year from date of manufacture.

Coverage

Approximate coverage per one-gallon bottle, when used as a bonder, is 200 sq. ft. When used as an additive to cementitious stucco use 1-quart per 90 lb. bag of stucco.

Job Procedure

- A. Condition of Base:
 1. When used as a bonder, base must be clean and free of loose material or foreign matter. Remove all loose particles; disintegrated concrete; traces of oil, grease, dirt, dust, efflorescence, form treatments, foreign materials and other contaminants.
 2. When used as an additive, base must be prepared in accordance with stucco manufacturer's instructions.
- B. Mixing:
 1. Thoroughly mix LaHabra® Acrylic Bonder before using.
 2. Do NOT dilute before use.
- C. Application:
 1. Applied as a Bonder:
 - (a) Apply to properly prepared base by brush, spray or roller.
 - (b) Apply plaster coat while Acrylic Bonder is still tacky. This is within approximately 20 minutes, depending on weather and job conditions.
 - (c) If Acrylic Bonder is allowed to dry before the plaster coat can be applied, apply a second coat of Acrylic Bonder.
 2. Applied as an Additive: After thoroughly mixing LaHabra® Acrylic Bonder into the cementitious stucco in the proper amount, the stucco may be applied and finished in accordance with manufacturer's instructions.

Typical Physical Properties

Appearance	White, milky liquid
Solids content	40 to 44%
pH, when packed	9.5 to 10
Specific gravity	1.059
Density	8.8 lbs. U.S. gallon
Freeze/thaw stability	5 cycles minimum (freezing at 15°C; thawing at 25°C.)
Minimum film formation temperature	10 to 12°C

The above properties are typical only and should not be considered specifications.

Cautions and Limitations

- A. See package for handling precautions.
- B. Always wear proper safety equipment, including particle mask, when mixing and/or applying this product.



Corporate Office

ParexLaHabra Products, Inc.
P.O. Box 17866
Anaheim, CA 92817
4125 E. La Palma, Suite 250
Anaheim, CA 92807
Phone: 1-877-LHSTUCCO
Fax: 714-774-2079
Email: info@lahabrastucco.com
lahabrastucco.com

Sales Offices & Warehouses

Anaheim
P.O. Box 3700
1631 W. Lincoln Ave.
Anaheim, CA 92803
Phone: 714-774-1186
Fax: 714-774-8599

North Hollywood
8161 Lankershim Blvd.
North Hollywood, CA
91605-1611
Phone: 818-504-9180
Fax: 818-504-1985

Northern California
11290 South Vallejo Court
French Camp, CA 95231
Phone: 209-983-8808
Fax: 209-983-8873

Riverside
2150 Eastridge Ave.
Riverside, CA 92507
Phone: 951-653-3549
Fax: 951-653-8189

Dallas
Warehouse
P.O. Box 188
Cresson, TX 76035
Phone: 972-820-8258
Fax: 972-467-5836
Customer Service
Phone: 1-877-LHSTUCCO
Fax: 714-774-8599

