PAREXUSA

Dry-Tex Sand Fine Dry-Tex Sand Coarse

DPR 300 Dry Acrylic Finish



DESCRIPTION:

- 100% Dry acrylic-based textured finish
- The non-tacky surface provides high resistance to accumulation of dirt, mold, and pollutants.
- Integrally colored with highquality pigments
- Tinted on-site with high quality pigments supplied in separate packaging

USES:

Exterior coat for:

- EIFS
- Properly prepared masonry, stucco, and concrete surfaces
- Interior application on:
- Drywall
- Properly prepared masonry and concrete.

COMPOSITION:

- Binder base: 100 percent acrylic polymer.
- Aggregate: Pure crushed marble, rust-free.
- VOC-compliant. Meets SCAQMD Rule 1113 when using Parex USA Non-VOC Colorants.
- Pigment base: Titanium dioxide.
- Color: Tinted to desired custom color.

COVERAGE:

Depending on the condition of the substrate and method of application, approximate coverage per bag is:

Sand Fine 150–165 ft² (14–15 m²)

Sand Coarse 110–125 ft² (10–11.5 m²)

CONTAINER:

40 lb (18.2 kg) net weight in multiwall bags.

- Storage: Store off the ground and protect from sun and moisture.
- Shelf life: Reference Parex USA Expiration Date of Products Technical Bulletin.

DRYING TIME:

24 hours under normal conditions. High humidity and low temperatures extend drying time.

CLEAN-UP:

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Concrete and masonry should have joints tooled flushed and be leveled before application of Dry-Tex for a consistent texture.
- Stucco brown coats shall be moist cured a minimum of 48 hours and for an additional 5 days after moist curing before application of Dry-Tex finishes.
- Any form-release agents or bond breakers must be removed. Concrete may be smoothed with a cementitious acrylic base coat.
- For interior drywall, prepare as for painting.

Parex USA, Inc. 4125 E. La Palma Ave., Suite 250 Anaheim, CA 92807 (866) 516-0061 Tech Support: (800) 226-2424



- Parex USA recommends the use of primer to enhance the appearance and uniformity of the finish, improved coverage, and decrease the chance of efflorescence. This is especially true when using dark colors or finishes with a large aggregate. If specified, prime with a Parex USA Primer, refer to Product Data Sheet.
- For additional options, contact Parex USA Technical Services Department.

MIXING:

- Use clean equipment for mixing and preparation.
- Add 1 1/4 Gal (4.73 L) of clean, cool, potable water to a clean 5 Gal (19 L) pail.
- Add all of the color from the tint vial. To ensure all of the color is used, fill empty color vial 1/3 full with water, close lid, shake, and empty into the mixing pail.
- Add 1/2 bag of Dry-Tex Finish and mix, using a heavy-duty 1/2 in. (13 mm.) drill with a rust-free paddle at 400-500 rpm.
- Mix until product is uniformly colored.
- Add remaining Dry-Tex Finish and a small amount of water, up to 1/4 Gal (0.95 L) as needed for workability and to obtain a desired finish texture. Mix to a uniform consistency.
- To avoid color variations add the same amount of water to each 40 lb. (18.2 kg.) bag of finish.

APPLICATION:

- Read the entire label before using this product.
- Always maintain a wet edge and work to corners or joints. For best color consistency, use finish with the same batch number within a wall section.
- Keep container closed when not in use.
- Use a clean stainless steel trowel and apply a uniform coat at a maximum thickness of the largest aggregate size of the finish.
- Texturing Sand Fine and Sand Coarse: Use a clean plastic float or stainless steel trowel. A plastic float will roll the large aggregates more than a stainless steel trowel. Occasionally clean and dry the plastic float or steel trowel while texturing. Use consistent pressure and motion to achieve the desired texture.

Facilities

French Camp, CA North Hollywood, CA Riverside, CA San Diego, CA Colorado Springs, CO Haines City, FL Duluth, GA Redan, GA

Spray application: To achieve consistent texture, spray application must use consistent motion, pressure, distance and spray angle. For best spray application results, two coats with drying between are recommended. A job-site mock up is advised.

LIMITATIONS:

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, and free from any residue that might affect the ability of the finish to bond to the surface.
- Some shrinkage is considered normal for applications greater than 1.5 mm.
- Application in direct sunlight in hot weather may adversely affect aesthetics.
- Best used shortly after mixing with water.
- Do not use with any non-Parex USA additive.
- Colors are matched at water usage listed. Any deviation could cause a shift in color.
- Must not be used on exposed exterior horizontal surfaces. Minimum slope is 27° or 6:12.
- Do not use on surfaces subject to hydrostatic pressure or continuous or intermittent water immersion.

WARNING

- Read complete Warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Safety Data Sheet (SDS). The most current SDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, Parex USA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Albuquerque, NM Allentown, PA San Antonio, TX